



POR-15 RESTOGRIP

Application Information

PRODUCT DESCRIPTION:

RestoGRIP® is an exceptionally dense body filler which bridges holes in all types of structural materials. Vacuum manufacturing insures no pinholes. 45% more flexible than other fillers. SAND RestoGRIP® after 20 minutes or within 4 hours of application; otherwise sanding will be more difficult due to RestoGRIP®'s incredible density and strength.

Surface Preparation:

Remove all foreign material from surrounding areas. If any wax, oils, grease are present, remove them with POR-15® Marine Clean (do not use solvent-based preps). If RestoGRIP® is intended to cover rusted areas, first paint area with POR-15® Rust Preventive Paint. Apply RestoGRIP® to POR-15® coating without sanding if POR-15® coating is less than 6 hours old. If POR-15® coating is more than 6 hours old, sand surface lightly with 300 grit paper, then apply RestoGRIP®. For perfectly smooth finish, apply a skim coat of StraightLine Body Filler and sand to desired result.

Flammable. Contains Styrene, Cas #100-42-5. Do not inhale. May irritate eyes and skin. Keep away from children. Keep in a cool place. Use only in well-ventilated areas.

Directions for Use:

Step 1: Measure out paste and hardener. As a guide to measuring, use one golf-ball size of filler to 3 pea-sizes of hardener.

Step 2: Mix paste and hardener together.

Step 3: Mix for one minute until both components blend into a uniform color.

Step 4: Apply the mixed paste to repair. The paste is useable until it begins to harden, usually after 5 to 10 minutes

Information contained herein is to our knowledge true and accurate, but all recommendations or suggestions are made without guarantee. Since the conditions of its use are beyond our control, RestoMotive Laboratories/POR-15, Inc. disclaims any liability incurred in connection with the use of its products and information contained herein. No person is authorized or empowered to make any statement or recommendation not contained herein, and any such statement or recommendation so made shall not bind the Corporation. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use, and no license implied or in fact is granted herein under the claims of any patents.